

**Amendments to the Claims:**

This listing of claims replaces any and all prior claim lists.

**Listing of Claims:**

Claim 1-2 (deleted).

Claim 3 (currently amended). A process ~~according to Claim 2, wherein the metal component to be adsorbed to the~~ for producing a luminescent glass selected from the group consisting of:

- (i) a process comprising the steps of adsorbing, to a porous high silica glass, is at least one member- metal component selected from the group consisting of V, Cr, Mn, Fe, Co, Ni, Cu, Ag, Sn, Eu, Ce and Tb; and thereafter heating the porous glass in a reducing atmosphere,
- (ii) a process comprising the steps of adsorbing, to a porous high silica glass, at least one metal component selected from the group consisting of elements of Groups IVA, VA, VIA, VIIA, VIII, IB, IIB and IVB of the Periodic Table; and thereafter heating the porous glass in a reducing atmosphere, and
- (iii) a process comprising the steps of adsorbing, to a porous high silica glass, at least one metal component selected from the group consisting of elements of Groups IIIA, IVA, VA, VIA, VIIA, VIII, IB, IIB and IVB of the Periodic Table; further adsorbing, to the porous glass, at least one element selected from the group consisting of B, N, F, Al, P and S; and thereafter heating the porous glass in a reducing atmosphere.

Claim 4 (deleted).

Claim 5 (deleted).

Claim 6 (deleted).

Claim 7 (deleted).

Claims 8-9 (deleted).

Claim 10 (currently amended). A luminescent glass ~~according to Claim 9, obtained~~ by a process comprising the steps of adsorbing, to a porous high silica glass, at least one metal component selected from the group consisting of elements of Groups IIIA, IVA, VA, VIA, VIIA, VIII, IB, IIB and IVB of the Periodic Table; and thereafter heating the porous glass in a reducing atmosphere;

the luminescent glass comprising at least 96 wt.% of SiO<sub>2</sub>, 0.5 to 3 wt.% of B<sub>2</sub>O<sub>3</sub>, 0.1 to 1.5 wt.% of Al<sub>2</sub>O<sub>3</sub>, and 50 to 2000 ppm of at least one metal component selected from the group consisting of elements of Groups IIIA, IVA, VA, VIA, VIIA, VIII, IB, IIB and IVB of the Periodic Table.

Claim 11-13 (deleted).

Claim 14 (new). A luminescent glass according to Claim 10, wherein the metal component to be adsorbed to the porous high silica glass is at least one member selected from the group consisting of elements of the fourth period of the Periodic Table, elements of the fifth period of the Periodic Table, and lanthanoids.

Claim 15 (new). A luminescent glass according to Claim 14, wherein the metal component to be adsorbed to the porous high silica glass is at least one member selected from the group consisting of V, Cr, Mn, Fe, Co, Ni, Cu, Ag, Sn, Eu, Ce and Tb.

Claim 16 (new). A luminescent glass according to Claim 10, wherein the metal component to be adsorbed to the porous high silica glass is a rare earth element or elements.

Claim 17 (new). A luminescent glass according to Claim 10, wherein the metal component to be adsorbed to the porous high silica glass is at least one metal component selected from the group consisting of elements of Groups IVA, VA, VIA, VIIA, VIII, IB, IIB and IVB of the Periodic Table.

Claim 18 (new). A luminescent glass according to Claim 10, wherein the heating temperature is 900 to 1600°C.

Claim 19 (new). A luminescent glass according to Claim 10, obtained by the process which further comprises, before the heating step, the step of adsorbing, to the porous glass, at least one element selected from the group consisting of B, N, F, Al, P and S.

Claim 20 (new). A luminescent glass according to Claim 10, wherein the porous high silica glass is obtained by causing phase separation of an alkali borosilicate glass by heat treatment and then treating the phase-separated glass with an acid.

Claim 21 (new). A lighting system for use in water or air, comprising a luminescent glass and an ultraviolet light source;

the luminescent glass being obtained by a process comprising the steps of adsorbing, to a porous high silica glass, at least one metal component selected from the group consisting of elements of Groups IIIA, IVA, VA, VIA, VIIA, VIII, IB, IIB and IVB of the Periodic Table; and thereafter heating the porous glass in a reducing atmosphere.

Claim 22 (new). A lighting system according to Claim 21, wherein the luminescent glass is obtained by the process which further comprises, before the heating step, the step of adsorbing, to the porous glass, at least one element selected from the group consisting of B, N, F, Al, P and S.

Claim 23 (new). A lighting system comprising a luminescent glass disposed in water; an ultraviolet light source placed outside water; and an optical fiber provided so that one end of the optical fiber connected to the ultraviolet light source and the other end is located in the vicinity of the luminescent glass;

the luminescent glass being obtained by a process comprising the steps of adsorbing, to a porous high silica glass, at least one metal component selected from the group consisting of elements of Groups IIIA, IVA, VA, VIA, VIIA, VIII, IB, IIB and IVB of the Periodic Table; and thereafter heating the porous glass in a reducing atmosphere.

Claim 24 (new). A lighting system according to Claim 23, wherein the luminescent glass is obtained by the process which further comprising, before the heating step, the step of adsorbing, to the porous glass, at least one element selected from the group consisting of B, N, F, Al, P and S.

Claim 25 (new). A display device comprising, as a luminous body, a luminescent glass obtained by a process comprising the steps of adsorbing, to a porous high silica glass, at least one metal component selected from the group consisting of elements of Groups IIIA, IVA, VA, VIA, VIIA, VIII, IB, IIB and IVB of the Periodic Table; and thereafter heating the porous glass in a reducing atmosphere.

Claim 26 (new). A display device according to Claim 25, wherein the luminescent glass is obtained by the process which further comprises, before the heating step, the step of adsorbing, to the porous glass, at least one element selected from the group consisting of B, N, F, Al, P and S.